

MATERIAL DATA SHEET			MDS D53	Rev. 4
TYPE OF MATERIAL: Ferritic/Austenitic Stainless Steel, Type 25Cr duplex				
PRODUCT	STANDARD	GRADE	ACCEPT. CLASS	SUPPL. REQ.
Wrought fittings	ASTM A 815	UNS S32550 UNS S32750 UNS S32760	WP-S, WP-WX and WP-W	S7
HIP products	ASTM A 988	UNS S32505		
				Page 1 of 2
1. SCOPE	This MDS specifies the selected options in the referred standard and additional requirements which shall be added or supersede the corresponding requirements in the referred standard. This MDS is based on the mechanical properties of UNS S32760.			
2. QUALIFICATION	Manufacturers and the manufacturing process used for manufacturing of product to this MDS shall be qualified in accordance with NORSOK Standard M-650.			
3. STEEL MAKING	The steel melt shall be refined with AOD or equivalent.			
4. MANUFACTURING PROCESS	The manufacturing of products according to this MDS shall be carried out according to the M-650 qualified manufacturing procedure. The Hot Isostatic Pressed (HIP) process is an acceptable alternative manufacturing process.			
5. HEAT TREATMENT	Solution annealing followed by water quenching. Fittings shall be placed in such a way as to ensure free circulation of air and water around each fitting during the heat treatment process including quenching.			
6. CHEMICAL COMPOSITION	PREN = % Cr + 3.3 % Mo + 16 % N ≥ 40.0			
7. TENSILE TESTING	Base material properties: $R_{p0.2} \geq 550$ MPa; $R_m \geq 750$ MPa; $A \geq 25$ %			
8. IMPACT TESTING	Charpy V-notch testing according to ASTM A 370 at - 46 °C is required for the thickness ≥ 6 mm. The minimum absorbed energy shall be 45 J average / 35 J single. Reduction factors for sub-size specimens shall be: 7.5 mm -5/6 and 5 mm -2/3. The notch location and number of specimen shall be: Seamless fittings: One set, (3 specimens). Welded fittings: Two sets, (each 3 specimens) one located in base material and one in weld metal.			
9. CORROSION TEST	Corrosion test according to ASTM G 48 Method A is required. Test temperature shall be 50 °C and the exposure time 24 hours. The test shall expose the external and internal surfaces and a cross section including weld zone (if relevant) in full wall thickness. Cut edges shall be prepared according to ASTM G 48. The whole specimen shall be pickled before being weighed and tested. Pickling may be performed for 5 minutes at 60 °C in a solution of 20 % HNO ₃ + 5 % HF. The acceptance criteria are: - No pitting at 20 X magnification. - The weight loss shall be less than 4.0 g/m ² .			
10. MICROGRAPHIC EXAMINATION	The micrographic examination shall cover the near surfaces and mid-thickness region. For welded fittings both the weld and the base material is required examined. The ferrite content shall be determined according to ASTM E 562 or equivalent and shall be within 35-55 % for base material and 35-65 % for weld metal. The microstructure, as examined at minimum 400 X magnification on a suitably etched specimen, shall be free from intermetallic phases and precipitates.			
11. EXTENT OF TESTING	Tensile testing, impact testing, hardness testing, corrosion testing and microstructure examination shall be carried out for each heat and heat treatment load within a wall thickness range of 5 mm and welded with the same WPS.			
12. TEST SAMPLING	Samples for production testing shall realistically reflect the properties in the actual components. Test sampling shall be made from an actual fitting or from a prolongation thereof. Sketches shall be established showing location for extraction of test specimens.			
13. WELDING	The PQR/WPQR shall be qualified in accordance with ASME IX or ISO 15614-1 and shall include the same examinations as for the production testing. The qualification shall be carried out on the			

MATERIAL DATA SHEET			MDS D53	Rev. 4
TYPE OF MATERIAL: Ferritic/Austenitic Stainless Steel, Type 25Cr duplex				
PRODUCT	STANDARD	GRADE	ACCEPT. CLASS	SUPPL. REQ.
Wrought fittings	ASTM A 815	UNS S32550 UNS S32750 UNS S32760	WP-S, WP-WX and WP-W	S7
HIP products	ASTM A 988	UNS S32505		
				Page 2 of 2
	same material grade (UNS number) as used in production. Change of specific make (brand name) of welding consumables requires requalification.			
14. NON DESTRUCTIVE TESTING	<p>Supplementary requirements S7, penetrant testing, shall apply to 10 % of seamless (from the test lot as defined above) and 100 % of welded fittings above NPS 2.</p> <p>The examination shall be carried out after calibration and pickling. For welded fittings the examination shall cover the weld only. The weld of each examined fitting shall be ground flush in a length of 100 mm prior to penetrant testing. The acceptance criteria shall be ASME VIII, Div. 1, Appendix 8.</p> <p>NDT operators shall be certified in accordance with EN 473 or equivalent.</p>			
15. SURFACE FINISH	White pickled.			
16. REPAIR OF DEFECTS	Weld repair of base material is not acceptable. For repair of welds the same requirements to PQR/WPQR shall apply as for production welding.			
17. MARKING	The component shall be marked to ensure full traceability to melt and heat treatment lot.			
18. CERTIFICATION	<p>The material manufacturer shall have a quality system certified in accordance with ISO 9001 and the system shall have undergone a specific assessment for the relevant materials.</p> <p>The material certificate shall be in accordance with EN 10204 Type 3.1, and shall include the following information:</p> <ul style="list-style-type: none"> - Manufacturer of the starting material for the finished product; - Steel manufacturer, melting and refining practice; - Heat treatment condition. (Solution annealing temperature and holding time shall be stated). 			